


Dynatec, LLC

SAMPLE: 5.88% MPG+ (Lab# 17082824) blended with
94.12% formula Mobil 1 15W50 (Lab# 17091306) by weight
Four Ball Wear With Coefficient of Friction



Method ASTM D4172 1200 RPM, 40 kg Load, 1 Hour @ 75°C
Wear Scar = 0.70 mm Grand Average = 0.055 Y-O Intercept = 0.060